

### Product Information Sheet

#### Product

## Polymex® PK3I3

#### Product Description


Polymex® PK3I3 is a peelable lidding film with a one side external heat seal and an internal corona treated surface to promote adhesion. Polymex® PK3I3 is ideal for use in the application of food packaging, specifically chilled or frozen foods such as ready meals where high transparency is required (self-test recommended). In addition the food contact approval allows it to be used in food contact applications.

Available in thicknesses 15, 20 and 25 micron.

#### Key Features

- Excellent clarity, low haze, heat sealable
- Ideal for food packaging, laminating and printing
- Heat seals to itself, CPET, APET, GPET, paperboard and PVC
- No solvents, contamination and odour free

#### Structure of Polymex® PK3I3



Property	Test Method	Unit	Value		
Film Thickness	-	micron	15	20	25
Film Yield	-	M <sup>2</sup> /Kg	48	36	28
Unit Weight	-	g/m <sup>2</sup>	21	28	36
Haze	ASTM D 1894-78	%	10	12	14
Tensile strength at break MD TD	ASTM D 822-83	MPa	172 159		
Elongation at break MD TD	ASTM D 1897-78	%	135 95		
Heat seal strength	CPET @ 130°C, 166KPa psi, 2 seconds	g/15 mm	266		
Coefficient of friction (static)	ASTM D 1894-78	-	0.2		
Shrinkage MD TD	at 300°F/30min	%	1 0.2		

'MD' - Machine direction. 'TD' - Transverse direction

#### Applications

Polymex® PW122 complies with EU food contact legislation 2002/72/EC, and amendments with FDA regulation 21 CFR 177.1630

*The information above is given in good faith and should be considered as a guide not a specification.*



BS EN 14644 : 1999  
CLEANROOM CLASS 8

+44 (0) 20 7740 9740  
[www.packagingfilm.co.uk](http://www.packagingfilm.co.uk)