

Product Information Sheet

Product

Polymex® PP20N

Product Description


Polymex® PP20N is a bi-axially oriented, co-extruded, clear untreated film. Polymex® PP20N is ideal for use in applications where high transparency is required, such as gloss laminations, adhesive tapes, decorative films and insulation tapes where the treated surface offers a fantastic blank canvas for sensitizing and metallizing (self-test recommended). In addition the food contact approval allows it to be used in food contact applications.

Available in thicknesses 12 – 75 micron.

Key Features

- Excellent Clarity
- Ideal for sensitizing, laminating, or adhesive coating
- Good for coating, packaging and as a release film for thermosetting resins

Structure of Polymex® PP20N



Property	Test Method	Unit	Value	
Film Thickness	-	micron	12	23
Film Yield	-	M ² /Kg	59	31
Unit Weight	-	g/m ²	17	32
Haze	ASTM D 1003-61	%	2.0	2.2
Tensile strength at break MD TD	ISO 527-1-2	N/mm ²	250 260	250 260
Elongation at break MD TD	ISO 527-1-2	%	120 105	120 110
Density	ASTM D 1505-68	g/cm ³	1.4 (23°C)	
Coefficient of friction (static)	ASTM D 1894	-	0.4	
Shrinkage MD TD	150°C, 15 min	%	1.4 0.2	1.3 0.1

'MD' - Machine direction. 'TD' - Transverse direction

Applications

Polymex® PW122 complies with EU food contact legislation 2002/72/EC, and amendments with FDA regulation 21 CFR 177.1630

The information above is given in good faith and should be considered as a guide not a specification.



BS EN 14644 : 1999
CLEANROOM CLASS 8

+44 (0) 20 7740 9740
www.packagingfilm.co.uk